

CHEVRON GROUP II/II+ BASE OILS



FOR FORMULATING PREMIUM PRODUCTS

Chevron Group II/II+ base oils are ideal choices for lubricant manufacturers seeking to meet tightening specifications, optimize blending alternatives and maximize automotive and industrial products they formulate for the market. In short, these products provide excellent value for blenders.

PURITY FOR PERFORMANCE AND SAVINGS

The quality of base oil depends on the manufacturing process. Chevron's high-purity Group II/II+ base oils, produced with the company's patented ISOCRACKING®/ISODEWAXING®/ISOFINISHING® technologies, can help lubricant formulators meet stringent US and European technical requirements.

These base stocks have exceptional oxidation stability, low volatility in their viscosity grade and are essentially sulfur-free. As a result, you can produce a broad viscosity range of higher performing lubricants while minimizing or completely eliminating the need for more expensive Group III base oils.

MANUFACTURED GLOBALLY FOR SUPPLY RELIABILITY

Chevron produces a full slate of premium Group II/II+ oils at two strategically located refineries, with a third plant under construction. These base oils are shipped to four regional supply hubs, which serve the world's most significant lubricant markets.

HDMO

BALANCE FUEL ECONOMY WITH WEAR PROTECTION

Fuel economy improves when lubricants are blended with lower viscosity base oils. But large diesel engines, operating at low speeds and very high torque, need heavy-duty lubrication. Chevron premium Group II/II+ base oils fill the performance gap. With higher viscosity

for extended wear protection, the purity to meet tightening environmental regulations, and being effectively sulfur-free, they are preferred for meeting Mid and Low SAPS HDMO requirements in Europe.

PCMO

LOWER FORMULATING COSTS WITH GROUP II/II+/III BLENDS

You can lower costs for your largest volume lubricants by blending with up to 100% Group II/II+ base oils. Through precise formulation work with your additive company, the level of Group III can be optimized, and in some cases eliminated, for cost savings with no compromise in performance.

IMPROVE ECONOMICS, TRANSITION TO MULTIGRADE

To improve fuel economy, lubricant marketers in emerging markets are transitioning from monograde or heavy multigrade motor oils to lighter, premium-quality lubricants. In many heavier PCMO formulations, you can replace Group I with Group II/II+ for reduced costs and simplified blending. As you move to 5W lubricants, blending with Group II/II+ enables you to minimize the amount of Group III needed.

INDUSTRIAL OILS

EXTEND OIL LIFE, IMPROVE PERFORMANCE

Industrial oils often require heavier base stocks, but in some applications the purity and oxidation stability of Chevron's Group II base oils can boost performance significantly. In those cases, replace Group I base oils with Group II, and extend oil life by as much as 300%, typically with minimal or no requalification cost. If you're formulating with Group III base stocks, in most situations you can substitute a lower-cost Group II without losing performance. Major additive companies are experienced at optimizing industrial oil performance with Chevron base oils.



All trademarks are the property of Chevron Intellectual Property LLC.

Renkert Oil, LLC

+1 (800) 423 6457 • +1 (610) 901 0025

www.RenkertOil.com

CHEVRON GROUP II/II+ BASE OILS — CONTINUED



GROUP II/II+ TEST DATA

Chevron's premium base oils have exceptional oxidation stability, low volatility for a given viscosity grade and are virtually sulfur-free, making them an excellent choice for blending high-performance, low-SAPS automotive engine oils, as well as process and industrial oils.

Typical Properties	Methods	100R	220R	600R	110RLV
API Base Oil Category	API 1509 E.1.3	Group II	Group II	Group II	Group II+
Appearance	SM 360-99	Bright & Clear	Bright & Clear	Bright & Clear	Bright & Clear
Color	ASTM D 1500	L0.5	L0.5	L0.5	L0.5
API Gravity, deg.	ASTM D 4052	34.4	31.9	31.2	35.4
Density, lb/gal	ASTM D 4052	7.10	7.22	7.28	7.06
Density, kg/l	ASTM D 4052	0.853	0.867	0.874	0.848
Specific Gravity @ 60°F/60°F	ASTM D 4052	0.853	0.867	0.874	0.848
Viscosity @ 40°C, cSt	ASTM D 445	20.3	43.7	108	21.1
Viscosity @ 100°C, cSt	ASTM D 445	4.1	6.6	12.2	4.38
Viscosity @ 100°F, SUS	ASTM D 2161	107	214	590	113
Viscosity Index	ASTM D 2270	102	102	103	118
CCS @ -20°C, cP	ASTM D 5293	N/A	3400	N/A	822
CCS @ -25°C, cP	ASTM D 5293	1400	5600	N/A	1350
CCS @ -30°C, cP	ASTM D 5293	2650	N/A	N/A	2450
Pour Point, °C	ASTM D 5950/1C	-15	-13	-17	-15
Flash Point, COC, °C	ASTM D 92	206	230	270	216
Volatility, wt. % distilled at 700°F/371°C	ASTM D 2887	13	N/A	N/A	N/A
Evaporative loss, Noack, wt.%	ASTM D 5800 (B)	26	10	2	16
Water, ppm	ASTM D 6304-98	<50	<50	<50	<50
Sulfur, ppm	ICP/XRF	<10	<10	<10	<10
Saturates, HPLC wt.%	Chevron	>99	>99	>99	>99
Aromatics, HPLC wt.%	Chevron	<1	<1	<1	<1

Contact us to request a sample or get more information about specifications, applications and delivery.

Renkert Oil, LLC

+1 (800) 423 6457 • +1 (610) 901 0025

www.RenkertOil.com