

VOLTRO™ II ELECTRICAL INSULATING OIL



Voltro II meets or exceeds ASTM Type II and Doble Tops transformer oil requirements. Voltro II provides exceptional oxidation stability to help extend the life of a transformer with minimal maintenance.

PRODUCT FEATURES

Voltro II is an inhibited insulating and cooling oil for power and distribution transformers and other equipment that requires extra oxidation protection.

An added oxidation inhibitor, 2,6-ditert-butyl-p-cresol (DBPC or BHT) minimizes sludge and acid. As a result, components can operate longer and at higher temperatures, extending the transformer's operating life.

PARAFFINIC ADVANTAGES

Renkert Oil's Voltro II is a highly-refined mineral oil, derived from paraffinic crude. It is severely hydro treated and inhibited providing a high flash point, high viscosity index and high oxidation stability characteristics. Paraffinic oils have excellent oxidation stability and thermal properties.

Voltro II Electrical Insulating Oil:

- meets or surpasses ASTM D3487
- conforms to corrosive test ASTM D 3487 method B
- passes corrosive sulfur IEC 62535 CIGRE
- is certified PCB free
- is DBDS free
- is passivator free
- is metal deactivator free
- is silicone free
- is a stable, low moisture oil
- has a high flash point

DISTRIBUTION

- Reliable US and global distribution
- Convenient delivery by ship, truck, rail, drums or flexi bags

APPLICATIONS

- Power & distribution transformers
- Switchgear & circuit breakers
- Rectifiers

Contact us to request a sample or for additional details on Voltro II for your application. Renkert Oil's expert consultants are also happy to provide troubleshooting or problem solving assistance.

All trademarks are the property of Renkert Oil, LLC.

Renkert Oil, LLC

+1 (800) 423 6457 • +1 (610) 901 0025

www.RenkertOil.com



VOLTRO II ELECTRICAL INSULATING OIL SPECIFICATION

This electrical insulating oil is produced from a severely hydrotreated oil to meet the specification requirements defined in ASTM D 3487.

RENKERT OIL VOLTRO™	ASTM TEST METHOD	ASTM TYPE II SPEC		VOLTRO™ II TYPICALS
		Minimum	Maximum	
Physical Properties				
Viscosity @ 100 °C, cSt	ASTM D 445		3.0	2.5
Viscosity @ 40 °C, cSt	ASTM D 445		12.0	9.3
Pour Point, °C	ASTM D 97		-40.0	-45
Flash Point, COC, °C	ASTM D 92	145		175
Specific Gravity @ 15°C/15°C	ASTM D 1298		0.9100	0.83
Neutralization Number, mg KOH/gm	ASTM D 974		0.03	<.01
Interfacial Tension @ 25 °C, dynes/cm	ASTM D 971	40		50
Karl Fischer Water, ppm	ASTM D 1533		35.0	12
Inhibitor Content, %	ASTM D 2668	0.15	0.30	0.19
Electrical Properties				
Dielectric Breakdown @ 60 Hz, disk electrodes kV	ASTM D 877	30		45
Dielectric Breakdown at 60 Hz, VDE, kV (2.03-mm) gap	ASTM D 1816 (a)	35		53
Power Factor, % @ 25 °C	ASTM D 924		0.05	0.005
Power Factor, % @ 100 °C	ASTM D 924		0.30	0.1
Gassing Tendency, µL/min	ASTM D 2300		30	16
Chemical Properties				
Oxidation Stability	ASTM D 2440			
72 hr: Sludge, % by mass			0.1	<.01
Total Acid Number, mg KOH/g			0.3	<.01
164 hr: Sludge, % by mass			0.2	<.01
Total Acid Number, mg KOH/g			0.4	<.01
RBOT, min	ASTM D 2112	195		350
Corrosive Sulfur	ASTM D 1275B	Non-corrosive		Pass
Corrosive Sulfur CIGRE	IEC 62535	Non-corrosive		Pass
Aniline Point, °C	ASTM D 611	63.0		88
PCB Content, ppm	ASTM D 4059	None detected		ND
Appearance		Clear / No Particulates		Clear